






## P 9 Multi

Synthetic Fiber with PTFE Impregnation and Silicone free dynamic Run In Lubricant

### Characteristics

- High fatigue strength and flexibility
- Good acid resistance (e. g. hydrofluoric acid 15% / 50 °C)
- High cross section density through PTFE blocking agent, good for crystallizing media
- Recommended shaft surface hardness: HRC 35
- Good pliability, therefore perfect adaption of uneven shaft surfaces

### Operating range

			
p [psi]	290	870	1450
v [fpm]	2950	390	
t °F	-60 ... +540		
pH	1 - 13		
lb/in <sup>3</sup>	0.0488		

Practical useful application data:  
max. temperature: +360 °F

### Main application

- Centrifugal pumps
- Mixer
- Kneader
- Agitators
- Filter
- Extruder
- Refiner

### Suitable for

- Chemical industry
- Sugar industry
- Pulp and paper industry



### Form of delivery

This packing can be manufactured from 4 to 40 mm / 3/16" to 1.5" square as well as in intermediate, inch sizes and special measurements.

- 04-09 mm/3/16"-5/16" on 2 lbs spool
- 10-15 mm/3/8"-9/16" on 5 lbs spool
- 16-25 mm/5/8"-1" on 10 lbs spool

Special length, pre-cut or die formed rings on request.

1 lbs of packing of the following cross-sections is equivalent to displayed lengths in feet:

Size	Feet	Size	Feet
4	68.9	13 [1/2"]	6.8
5 [3/16"]	44.1	14 [9/16"]	5.6
6	30.6	15	4.9
6.4 [1/4"]	27.3	16 [5/8"]	4.3
8 [5/16"]	17.2	18	3.4
9.5 [3/8"]	12.2	19 [3/4"]	3.1
10	11.0	20	2.8
11 [7/16"]	8.9	22 [7/8"]	2.3
12	7.7	25 [1"]	1.8

All technical information and advice is based on our experience and will be given most conscientiously but without any liability.

Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time. Please note that the technical values cannot be used all at the same time in their maximum values.

### ProPack AG

Rudolf-Diesel-Ring 28 . 82054 Sauerlach . Germany

Phone ++49 (0) 8104 6640 0 . Fax ++49 (0) 8104 6640 44  
propack@propack.ag

[www.propack.ag](http://www.propack.ag)  
TECHNOLOGY MADE IN GERMANY